

L9 ANSWER 3 OF 29 CAPLUS COPYRIGHT 2003 ACS on STN

ACCESSION NUMBER: 2000:393004 CAPLUS

DOCUMENT NUMBER: 133:31874

TITLE: Antireflective agents, films for protecting polarizing
panels and the panels

INVENTOR(S): Nakai, Hideyuki; Takiyama, Nobuyuki; Kobayashi, Toru;
Hasegawa, Mitsuyo

PATENT ASSIGNEE(S): Konica Co., Japan

SOURCE: Jpn. Kokai Tokkyo Koho, 17 pp.

CODEN: JKXXAF

DOCUMENT TYPE: Patent

LANGUAGE: Japanese

FAMILY ACC. NUM. COUNT: 1

PATENT INFORMATION:

PATENT NO.	KIND	DATE	APPLICATION NO.	DATE
JP 2000159840	A2	20000613	JP 1998-336193	19981126
PRIORITY APPLN. INFO.:			JP 1998-336193	19981126

AB The agents with good adhesion to transparent substrate surface and resistance to scratching, are obtained from F-contg. monomers selected from fluoro(cyclo)alkyl (meth)acrylates, YOOCCH:CR1COOZ [R1 = H, Me; Y, Z = (F-contg.) C2-12 alkyl, (F-contg.) C4-12 cycloalkyl (provided at least either Y or Z contains F)], CH2C(COOY)CH2COOZ, or/and F-contg. esters of 4,5-dicarboxycyclohexene. Thus, coating a soln. contg. dipentaerythritol hexaacrylate 60, dipentaerythritol hexaacrylate dimer 20, dipentaerythritol hexaacrylate oligomer (.gtoreq.3) 20, diethoxybenzophenone UV initiator 2, a ***silicone***
surfactant 1, Aerosil R 972 (treated fumed silica) 50, MEK 50, AcOEt 50 and i-PrOH 50 parts on the surface of a Konitac 80UVSH (cellulose triacetate) film, irradiating with UV light, coating on top with a soln. contg. 3,3,4,4,5,5,6,6-octafluorohexyl methacrylate 45, 2,2,3,3,4,4,5,5,6,6,7,7,8,8,9,9-heptafluorononylene glycol diacrylate 45, dipentaerythritol hexaacrylate 10, diethoxybenzophenone 0.2, F 177 (F-contg. ***surfactant***) 1, cyclohexanone 3500 and i-PrOH 7700 parts, drying and irradiating with UV light gave a coated film with reflective index 1.37, cross-cut adhesion 100/100 and good resistance to scratching.

EV979440200